



<b>D2090130P5</b>
<b>Pink Dielectric Powder</b>

### PRODUCT DESCRIPTION

This product is part of a range of Heat Curable Powders designed specifically for use in **Electro Luminescent** systems. These products are based on a unique curing process that results in the low temperature formation of a thermosetting polymer.

#### Product Benefits

Excellent adhesion to ITO, chemical and environmental resistance. This dielectric has been designed to be used with Phosphor C2080211P2 to produce a white light.

### PROCESSING

#### Screen Printing Equipment

Semi-Automatic, manual

#### Powder Screen Life

>3 hours

#### Screen Types

Stainless steel, polyester

#### Typical Curing Conditions

Belt Dryer 130°C for 3 minutes.  
Box Oven 130°C for 10 minutes.

#### Clean Up Solvent

Ethoxy Propanol or Sericol

#### Substrate

ITO coated polyester.

#### Storage

The product should be kept sealed, in its container, and stored at room temperature (20°C)

#### Shelf Life

In a sealed container, stored correctly, the shelf life is minimum 6 months from despatch.

#### Diluent/ Thinner

Not recommended.

### PHYSICAL PROPERTIES

<b>Colour</b>	Pink
<b>Solids Content</b> at 150°C	72.5 - 76.5%
<b>Viscosity</b> Haake RS1 C20/2° TiL at 230 sec <sup>-1</sup> at 25°C.	1.2– 3.0 Pa.sec
<b>Coverage</b> 1st Layer	242 cm <sup>2</sup> per g
2nd Layer Using a 230 mesh stain- less steel screen	260 cm <sup>2</sup> per g

### PHYSICAL PROPERTIES PRINTED ON POLYESTER FILM

<b>Cured film thickness</b> Double layer on 175µ ITO coated Polyester	20 microns
---	------------

### SAFETY AND HANDLING

These powders are intended for industrial use by trained personnel. It is important for workers to avoid overexposure to chemicals contained in these products.

Read the Material Safety Data Sheet (MSDS) and product labels before using the products.

Keep product container closed when not in use to prevent solvent evaporation and spilling hazard

Issued by Gwent Group March 2018  
Issue 6

Our Products are intended for sale to professional users. The information herein is general information designed to assist customers in determining the suitability of our products for their applications. All recommendations are made without guarantee, since the application and conditions of use are beyond our control. We recommend that customers satisfy themselves that each product meets their requirements in all respects before commencing a print run. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In no event shall Sun Chemical be liable for damages of any nature arising out of the use or reliance upon this information. Modifications of the product for reasons of improvements might be made without further notice.